

TURINO – SK(E) – FOLIE /Zitra - Fol

Technical Data Sheet

Physical and Chemical Properties/Typical Performance Characteristics

Chemical base	Dispersion Adhesive
Color (CQP 001-1)	Milky white film clear and transparent
Density (CQP 006-6)	Approx.1,0 kg/l
PH value (CQP 004-1)	Approx. 6
Viscosity at 20°C (Brookfiled) RVT, Sp. 5/5 Upm	Approx. 28000 mPas, medium viscosity
Solids content (CQP 002-2)	Approx. 55 %
Application temperature	15 – 25°C
Order weight (typical value)	5 – 100 g/m ²
Drying time (CQP 565-1) (Ventilation time before joining)	Approx. 30 min. bei 100 u (bei RT ²)
Drying temperature	Up to max. 120°C
Peel strength (CQP 568-1)	Approx. 6 N/25 mm
SAFT (CQP 560-1)	Approx. 160 °C

Description:

The adhesive used is a low adhesion, redetachable dispersion pressure sensitive adhesive with high aging resistance.

Product advantages:

- Easy processing
- Good removability
- High cohesion
- Wide adhesion spectrum
- High aging resistance
- Solvent-free

Scope of application:

The adhesive used is particularly suitable for applications where good removability is required. To test the adhesion and material compatibility tests must be carried out.

Legal notice:

The above information, in particular the proposals for processing and use of our products, are based on our knowledge and experience in the normal case, provided that the products have been stored and used properly. Because of the different materials, substrates and different working conditions a warranty of a work result or a liability, from whatever legal relationship, neither from these references, nor from an oral consultation can be justified, unless we acted in this regard intent or gross negligence falls. The user must prove that he has tested the products for suitability for the intended purpose.

Safety, health and environmental regulations / legislation specific for the substance or mixture

Ban / restriction

REACH - Restrictions on the manufacture, placing on the market and use of certain dangerous substances, preparations and articles (Annex XVII):	<i>inapplicable</i>
REACH list of substances of very high concern (Article 59):	<i>None of the components is listed (= > 0.1%).</i>
REACH - List of substances subject to authorization (Annex XIV):	<i>inapplicable</i>
REACH information:	<i>The substances contained in our products are - pre-registered or registered by our suppliers and or - pre-registered or registered by us and / or - exempted from the REACH regulation and / or - are subject to the REACH regulation, but are subject to registration excluded.</i>